


BioClean-C™ Fabric Technical Data Sheet

Basic Description:	Polyethylene/polypropylene laminate		
Basis Weight:	60gsm		
Colour(s):	Blue		



Fabric Physical Tests according to EN 14325: 2004						
Test Method	EN Class					
Abrasion Resistance EN530 Method 2	1 of 6					
Tear Resistance EN ISO 9073-4 (MD)	3 of 6					
Tear Resistance EN ISO 9073-4 (MD)	2of 6					
Tensile Strength ISO 13934-1 (MD)	2 of 6					
Tensile Strength ISO 13934-1 (MD)						
	1 of 6					
Puncture Resistance EN 863	1 of 6					
Other Fabric Physical Test						
Test			Result	Category (IEST-RP-CC003.3)		
Particle Shedding (Helmke Drum Test)			< 1700	Category 1		
Fabric Chemical Repellence EN ISO 6530						
Chemical			Result	EN Class		
30% Sulphuric Acid			>95%	3 of 3		
10% Sodium Hydroxide			>95%	3 of 3		
o-Xylene			>80%	1 of 3		
Butan-1-ol			>95%	3 of 3		
Fabric Chemical	Penetratio	on EN IS	SO 6530			
Chemical			Result	EN Class		
30% Sulphuric Acid			<1%	3 of 3		
10% Sodium Hydroxide			<1%	3 of 3		
o-Xylene			<1%	3 of 3		
Butan-1-ol			<1%	3 of 3		
Other Fabric Chemical Penetration ASTM739-12*						
Chemical Mean Breakthrough Time				/IBT), Minutes		
CIPLASTIN			>240			
CARMUSTINE		>240				
CYCLOPHOSPHAMIDE		>240				
DOXORUBICIN HYDROCHLORIDE			>240			
5-FLUOROURACIL			>240			
METHOTREXATE		>240				
ETHOPOSIDE		< 6				
PLACITACEL	>240					
THIOTEPA	55 (46, 88, 31)					
Fabric Blood, Body Fluids, Blood-borne Pathogens Penetration						
Test Method			Result			
Penetration by blood and body fluids - ISO 16603:200			Pa	SS		

^{*}Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 µg/cm²/min.Results achieved under controlled laboratory conditions, by accredited external testing laboratory.

Safety Note: All chemical tests and breakthrough times given relate to laboratory tests on fabrics only. Seams and closures may have lower breakthrough times, particularly when worn or damaged. It is the user's responsibility to select an appropriate garment, gloves, boots and other equipment for the particular use. The user shall be responsible for determining how long the garment can be worn for the particular use and whether it can be suitably cleaned for re-use. Ansell does not give any warranties or make any representations about its garments other than those contained in the official literature supplied by Ansell with

Penetration by blood-borne pathogens - ISO 16604:2004

Pass

Seam strength, inward leakage and spray tests are dependent upon the garment construction. This data is therefore available on the product specific data sheets.