

Permeation breakthrough times according to EN 16523-1:2015

CHEMICAL AGENT	CAS NUMBER	MEAN BREAKTHROUGH TIME (MINUTES)	PROTECTIVE INDEX	PART
Sodium Hydroxide NaOH 40%	1310-73-2	> 480	6	Palm
Methanol 99%	67-56-1	< 5	0	Palm
Hydrogen Peroxide 30%	7722-84-1	369	5	Palm
Formaldehyde 37%	50-00-0	>480	6	Palm

RATING SYSTEM						
0	1	2	3	4	5	6
<10	10-30	30-60	60-120	120-240	240-480	>480
NOT RECOMMENDED	SPLASH PROTECTION		MEDIUM PROTECTION		HIGH PROTECTION	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or on the cuff area if relevant. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. We wish to highlight that permeation times do not equate to safe wear time. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Contact your Ansell representative for ordering or more information.

North America
 US Tel: 800 952 9916
 CA Tel: 1-844-494-7854
 Email: insidesalesus@ansell.com

Central & South America
 Tel: +52(442) 296 20 50
 Email: cslac@ansell.com
Brazil
 Tel: +55-11-3356-3100
 Email: luvas.medicas@ansell.com

Europe, Middle East & Africa
 Tel: +32 (0) 2 528 74 00
 Email: info@ansell.eu

Asia Pacific
 Tel: +603 8310 6688
 Email: apac.medical@ansell.com

Australia & New Zealand
 Tel: +61 3 9270 7270
 Email: protection@ap.ansell.com