



# BioClean-D™ Overboots BDOB-L

## Overboots - Longer Length

Offering exceptional comfort and protection, the single-use BioClean-D longer (height 500mm) Overboots are constructed from antistatic low-linting CleanTough material, and feature a slip resistant sole and easy tie-fastenings at the top and ankle.

Please contact Ansell Customer Service for specific chemotherapy drug permeation times and recommendations.

### Key Features and Benefits

- Longer length - 500mm
- Low-linting
- Tie-fastenings at top & ankle
- Slip-resistant sole



### Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Pharmaceutical Manufacturing
- Biotechnology Manufacturing
- Medical Device Manufacturing
- Laboratory and Research





# BioClean-D™ Overboots BDOB-L

## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

<b>Material</b>	CleanTough™
<b>Audit Standards</b>	Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D
<b>Standards</b>	ASTM F739, CE 0598, EN ISO 13688:2013, EN 1149-5:2008, EN 13934-1, EN 13935-2, EN 530, EN 6530, EN 7854, EN 863, EN 9073-4, EN ISO 14325, Category III, EN 13034:2005 + A1:2009
<b>Packaging Overview</b>	30 pieces per sealed inner PE bag; one inner bag per sealed outer PE bag; five outer bags per lined carton (150 pieces)
<b>Country Of Origin</b>	China
<b>Cleanroom Class</b>	Class 10/ISO 4
<b>Shelf Life</b>	Five (5) years from date of manufacture.
<b>Construction</b>	Bound seams with single needle stitching
<b>Characteristics</b>	*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, and so are ideal for use in a static-safe environment.

### MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS
Abrasion Resistance	10 to 100 cycles	1
Flex Cracking Resistance	5,000 to 15,000 cycles	3
Trapezoidal Tear Resistance Cross Direction (CD)	CD 29.3 N	2
Trapezoidal Tear Resistance Machine Direction (MD)	MD 55.5 N	3
Tensile Strength Cross Direction (CD)	CD 48 N	1
Tensile Strength Machine Direction (MD)	MD 97 N	2
Puncture Resistance	8 N	1
Repellence to Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	96.3%	3
Repellence to Liquids - 10% NaOH	97.6%	3
Repellence to Liquids - O-Xylene	95.7%	2
Repellence to Liquids - Butan-1-ol	96.6%	3
Penetration by Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	0%	3
Penetration by Liquids - 10% NaOH	0%	3
Penetration by Liquids - O-Xylene	0%	3
Penetration by Liquids - Butan-1-ol	0%	3
Inward leakage of aerosols of fine particles <sup>1</sup>	Pass	N/A
Resistance to penetration by spray (Spray Test) <sup>1</sup>	Pass	
Seam Strength <sup>2</sup>	70 N	2
Electrostatic Charge Half Decay Time, t <sub>50</sub> (secs)	0.07	PASS

1. All interfaces with additional PPE were taped during testing, as required by the standards.
2. Seam not destroyed



# BioClean-D™ Overboots BDOB-L

## PARTICLE SHEDDING TEST RESULTS

TEST	RESULT
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <2000

## ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 Qg/cm <sup>2</sup> /min
CISPLATIN	>240
CARMUSTINE	<6
CYCLOPHOSHAMIDE	217 (275,162,215)
DOXORUBICINHYDROCHLORIDE	>240
5-FLUOROURACIL	>240
METHOTREXATE	>240
ETOPOSIDE	>240
PACLITAXEL	<10
THIOTEPA	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory.

## SIZE CHART

Universal

## ORDERING INFORMATION

	SIZE	Universal
BDOB-L	REORDER NO.	BDOB-L

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

### Asia Pacific Region

Ansell Global Trading Center  
T: +603 8310 6688  
F: +603 8310 6699

### North America Region

Ansell Healthcare Products LLC  
US T: +1 800 800 0444  
US F: +1 800 800 0445  
CA T: +1-800-363-8340

### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
T: +52 442 248 1544 / 248 3133

### Australia

Ansell Limited  
T: +61 1800 337 041  
F: +61 1800 803 578

### UK

Ansell Nitritex  
T: +44 1638 663338  
F: +44 1638 668890

## Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2022 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

